



## PRODUCT PROFILE

### DESCRIPTION

**COOL-TEX® CLEAR-GARD™** is an advanced, very low VOC water-based polyurethane coating system that provides superior performance and wear characteristics for COOL-TEX® coated floors, driveways, patios, and walkways. COOL-TEX® CLEAR-GARD™ combines the latest in water based polyurethane chemistry technology to provide a tough medium to high gloss finish surface for added beauty to floors.

COOL-TEX® CLEAR-GARD™ is both aesthetically pleasing and functional, as it protects the floor surface, increasing the life of the floor. COOL-TEX® CLEAR-GARD™ is designed to resist chipping, flaking and peeling, providing years of trouble-free service. COOL-TEX® CLEAR-GARD must be applied over COOL-TEX® base coat. It can be applied as one coat for a semi-gloss finish or two coats for a high gloss finish resulting in a durable, virtually maintenance-free coating that protects as well as it looks.

**CAUTION should be used when walking on any coated surface when it gets wet. Splatter or lace finishes, not the smooth roll-on finish, should be used for all application where water is present.**

### FEATURES

- High-Performance Water-Based Urethane Coating
- Use On Interior or Exterior Surfaces
- Stain and Scratch Resistant
- Low VOC
- UV Resistant

### BENEFITS

- Long-Lasting Durability
- Protects and Maintains Your COOL-TEX® Base Coat and the Concrete Beneath It From UV and Moisture.
- Breathable Coating Allowing Moisture Vapor to Escape
- Resistant to Most Garage Chemicals: Gasoline, Motor Oil, Anti-Freeze and Brake Fluid
- Resistant to Stains and Scratching
- Mildew, Fungus, and Algae Resistance Means Less Maintenance.

### RECOMMENDED PRIMERS/SUBSTRATES

COOL-TEX® Concrete Floor and Deck Base Coat.

## PRODUCT APPLICATION

### PREPATORY WORK

COOL-TEX® concrete floor and deck base coat should be completely dry and cured before applying the CLEAR-GARD™. Care must be taken to keep off the COOL-TEX® base coat prior to the CLEAR-GARD™ application. Unseen stains will be sealed in the film.

### AREA PROTECTION

The area should have already been properly protected due to the application of the COOL-TEX® base coat. If overspray occurs, clean immediately with water. Do not allow to dry, as removal will be difficult. All tape should be removed immediately after the final application.

### APPLICATION RATE

COOL-TEX® CLEAR-GARD™ should be applied as a two-coat system at a rate of 350-400 square feet per gallon per coat (allowing cure between coats) using a 3/8" nap high quality roller. Any additional coats will increase the gloss and deepen the final color. COOL-TEX® CLEAR-GARD is a 2-component water based polyurethane, and therefore Part-A & Part-B must be mixed thoroughly with the help of a mixing blade and drill just prior to the application. Begin mixing Part-A with drill, and slowly add Part-B, keeping a good vortex the entire time. Continue mixing for 2-3 minutes.

Once mixed, the material must be applied within two hours. Due to the nature of the material, workability is also limited to a two-hour period after it has been mixed. The CLEAR-GARD™ is applied by rolling the material evenly with a 3/8" nap high quality roller, then back rolled to force material into any voids and to achieve a pinhole-free coating.

**CARE MUST BE TAKEN TO HAVE ADEQUATE MANPOWER TO MAINTAIN WET EDGE WHEN ROLLING!**

### CLEAN-UP

Clean wet material immediately after use. Due to the nature of the material, it is extremely difficult to remove or clean once dry. It is important to use proper area protection and good painting practices to limit the amount of overspray from surrounding structures, landscaping and hard scraping. If over spray occurs, clean immediately with water. Do not allow to dry, as removal will be very difficult. Any dried overspray on glass should be carefully removed with a razor blade tool.

### DRYING/CURING TIMES

- Under Ideal Conditions:
- **Touch and Recoat:** 24 Hours at 70°F/50% RH
  - **Pot Life:** Two (2) Hours
  - **Dry Hard:** 24 Hours at 70°F/50% RH
  - **Full Cured:** 10-14 Days

**CAUTION:**  
Do NOT close the lid on any unused paint as pressure will build up in the can.

BEST PERFORMANCE

IMPORTANT STEPS

- Surface temperatures should be at least 55°F (7°C) and rising, and not to exceed 100°F (37.7°C).
- Do NOT apply when rain is imminent or expected within 12 hours or when the dew point is within 10 degrees of the temperature.
- TEX-COTE LLC does NOT promote the coating of any sealant joints, nor is the sealant compound an approved substrate.
- **DO NOT APPLY PRODUCT ANY HEAVIER THAN STATED OR A CLOUDY FILM MAY OCCUR. TAKE CARE TO ROLL EVENLY!**

BEST PERFORMANCE

| PHYSICAL PROPERTY | TYPICAL RESULT |
|-------------------|----------------|
| Carrier           | Water          |
| Volume Percent    | ~ 45%          |

| PHYSICAL PROPERTY              | TYPICAL RESULT |
|--------------------------------|----------------|
| VOC (grams/liters minus water) | <5 grams/liter |
| Weight/Gallon (pounds)         | 8.86 lbs       |

COOL-TEX® CLEAR-GARD™ | ASTM D1308 - Effect of Household Chemicals

| CHEMICAL               | TYPICAL RESULT |
|------------------------|----------------|
| Gasoline               | No Effect      |
| Motor Oil (Pennzoil)   | No Effect      |
| Antifreeze (Peak)      | No Effect      |
| Brake Fluid (Pennzoil) | No Effect      |
| Coffee (Black)         | No Effect      |

| CHEMICAL                      | TYPICAL RESULT |
|-------------------------------|----------------|
| Cola (Coca-Cola)              | No Effect      |
| Ketchup (Heinz)               | No Effect      |
| Mustard (Gulden's)            | No Effect      |
| Sun Tan Oil (Hawaiian Tropic) | No Effect      |
| 0.5 N Sodium Hydroxide        | No Effect      |

ORDER INFORMATION

PACKAGING

Available in 0.9 gallon (~200 square feet; 2-coat) kits. Part A and Part B must be mixed mechanically and thoroughly just prior to application.

COVERAGE RATES

Between 350-400 square feet per gallon per coat. Finish coats will vary depending upon desired look. For higher gloss, additional coats can be applied. **DO NOT THIN.**

SHELF LIFE

- 6-Month Shelf Life under proper conditions:
- Containers are sealed, upright and airtight in a dry place.
  - Maintain temperature of 45°F to 100°F (7°C to 37.7°C); AVOID FREEZING.
  - COOL-TEX® System heat-reflective only applicable for exterior applications.

SAFETY

WARNING

- CAUTION: Do NOT close the lid on any unused mixed material.

FIRST AID

- Ingestion: DO NOT INDUCE VOMITING.
  - If the person is conscious and has no trouble breathing, wash out the mouth with water and keep at rest.
  - Do NOT leave victim unattended.
  - Vomiting may occur spontaneously.
  - To prevent aspiration of swallowed product, lay victim on side with head lower than waist.
  - Do NOT give anything by mouth to an unconscious person.
  - IMMEDIATELY obtain medical attention.
- CAUTION should be used when walking on any coated surface when it gets wet.
- Splatter or lace finishes, not the smooth roll-on finish, should be used for all application where water is present.

## SAFETY

## VOC COMPLIANCE

All TEX-COTE® products comply with federal Volatile Organic Compound (VOC) rules and regulations.

Please contact your nearest TEX-COTE LLC office for assistance on the local and state VOC compliance in the area of intended use.

## WARRANTY

Upon completion of the application of the coating in accordance with the manufacturer's recommendations, TEX-COTE LLC will extend its limited commercial warranty for product replacement as a result of a defect in the material. The manufacturer must be notified prior to the application of the coating and the application must be in compliance with the manufacturer's recommendations for installation. TEX-COTE LLC shall have no obligation to contribute to or otherwise participate in labor or cost associated with effecting repairs. Specimen copy of material warranty is available upon request.

Corporate HQ & East Coast Facility 2422 E. 15th St., Panama City, FL 32405 | 800-454-0340 | 850-769-0347 | Fax 850-913-8619

South Florida Sales Office 7000 W. Palmetto Park Rd., Ste 210-W14, Boca Raton, FL 33433 | 954-581-0771 | Fax 954-581-9516

West Coast Facility 417 E. Weber Ave., Compton, CA 90222 | 323-233-3111 | Fax 310-438-2873